

CASE STUDY 81

HIRUSTAVERT DW 400 SPL – Rust Preventive for sheet metal component



PROFILE OF COMPANY

One of the renowned group in manufacturing of Auto and Sheet metal parts for all major Auto OEM's.



TRIAL OBJECTIVES

Rust prevention on Sheet Metal components for minimum 3 months in plant.



OPERATING / APPLICATION DETAILS:

1. RP oil is applied through spray on sheet metal pressed components
2. Material –CR Sheets EDD
3. Components are kept in shop floor environment
4. Trial duration 3 months



PRODUCT RECOMMENDED: HIRUSTAVERT DW 400 SPL

TRIAL RESULTS



No Rust observed on components after completion of three months.



10 % direct cost benefit achieved